



Photon Max™ With SRT™ Floor Finish



High Gloss Remarkable Response Floor Finish

Photon Max with Scuff Resistant Technology (SRT) is a highly repairable, low odor, black heel mark resistant floor finish. Designed for ultra high speed routine maintenance programs in high profile, high traffic areas. Photon Max with SRT provides a dramatic gloss response when burnished. Excellent leveling and low odor make it easy to apply.

Features

- Excellent "Off the Mop" Gloss
- Exceptional Response to Propane, Battery or Electric Equipment
- Extremely Low Odor
- Superior Black Heel Mark Resistance

Available In

4 - 1 Gal. Bottles Item #63204-00

55 Gal. Drum Item #63255-00

5 Gal Bag in Box Item #632B5-00

Directions for Use

Recommended for use on all types of resilient tile flooring and properly prepared hard surfaces.

RESTORATIVE MAINTENANCE:

Completely remove all old wax, finish and soil from floor surface following strip procedure instructions on Betco's #174; stripper label. Floor surface must be clean, dry and free of residue before finish is applied. Rinse with clean water if necessary. Apply finish in uniform, thin to medium coats using a clean synthetic finish mop, microfiber mop or applicator system. Allow each coat to dry thoroughly before applying additional coats, usually 20 - 30 minutes. Elevated temperatures, heavy coats and humidity may extend dry time. A minimum of 4 coats of finish is recommended.

NOTE: This product is a self-sealing finish; however, if tile is old, worn or porous, initially applying 1 - 2 coats of a Betco sealer will enhance gloss and long term performance.

ROUTINE MAINTENANCE:

Sweep large debris and dust mop. Damp mop or automatic scrub using a Betco floor cleaner. Buff or burnish the floor to enhance gloss as needed. Use Betco's #174; One Step High Speed Cleaner/Restorer to condition the floor and extend the time between top scrub and recoating.

INTERIM MAINTENANCE:

Sweep large debris and dust mop the floor. Top scrub the floor using Daily Scrub SC and maroon pad to remove the top soiled layers of finish. Floor surface must be clean, dry and free of residue before finish is applied. Apply 1 - 2 coats of finish as directed above. Please recycle empty container.

NOTE: Slip resistance meets or exceeds (ASTM D 2047-11) James Machine 0.5 minimum.

Tech Specs

Color (dried film)	Crystal Clear
Color (liquid)	White
Coverage	2000 - 3000 sq. ft./gallon
Dry time	20 - 30 minutes
Heel mark resistance	Excellent
Fragrance	Mild
Freeze/thaw stability	3 Cycles
Gloss (ASTM D1455-87)	One coat 85 - 90
Gloss (ASTM D1455-87)	Two coats 97 - 98
Free styrene content	0.0
Leveling	Outstanding
pH	8.2 - 8.9
Powdering resistance	Excellent
Warranty	2 years