



# Hi-Tech® Floor Finish



## Metal Interlocked Floor Finish

A floor finish breakthrough designed specifically to achieve outstanding performance when used in a high speed maintenance program. Hi-Tech's flexibility provides great adhesion to poured rubber sport floors as well.

### Features

Excellent wet look shine after burnishing  
Pressurized emulsified thermoplastics prevent powdering, scuffing and black marks.  
Self leveling and sealing.  
0.0% Free Styrene

### Available In

4 - 1 Gal. Bottles Item #61004-00

55 Gal. Drum Item #61055-00

5 Gal Bag in Box Item #610B5-00

### Directions for Use

Recommended for use on all types of resilient tile flooring and properly prepared hard surfaces.

### RESTORATIVE MAINTENANCE:

Completely remove all old wax, finish and soil from floor surface following strip procedure instructions on Betco's #174; stripper label. Floor surface must be clean, dry and free of residue before finish is applied. Rinse with clean water if necessary. Apply finish in uniform, thin to medium coats using a clean synthetic finish mop, microfiber mop or applicator system. Allow each coat to dry thoroughly before applying additional coats, usually 20 - 30 minutes. Elevated temperatures, heavy coats and humidity may extend dry time. A minimum of 4 coats of finish is recommended. Note: This product is a self-sealing finish, however, if tile is old, worn or porous, initially applying 1 - 2 coats of a Betco sealer will enhance gloss and long term performance.

### ROUTINE MAINTENANCE:

Sweep large debris and dust mop. Damp mop or automatic scrub using a Betco floor cleaner. Buff or burnish the floor to enhance gloss as needed. Use Betco's #174; One Step High Speed Cleaner/Restorer to condition the floor and extend the time between top scrub and recoating.

### INTERIM MAINTENANCE:

Sweep large debris and dust mop. Top scrub the floor using Daily Scrub SC and maroon pad or equivalent to remove the top soiled layers of finish. Floor surface must be clean, dry and free of residue before finish is applied. Apply 1 - 2 coats of finish as directed above.

Please recycle empty containers. Note: Slip resistance meets or exceeds standard, (ASTM D 2047-11) James Machine 0.5 minimum.

### Tech Specs

Buffability 300 RPM	Very Good
Buffability 1000 rpm	Excellent
Buffability 2000 rpm	Superb
Warranty	2 years
Color (liquid)	Milky white
Coverage	2000-3000 sq. ft./ gal.
Color (dried) film)	Water clear
Coverage	2,000 - 3,000 square feet/gallon
Drying time	20 - 30 minutes
Fragrance	Mild
Freeze/thaw stability	3 cycles
Gloss (ASTM D 1455-87)	2 coats 90 - 95
Gloss (ASTM D 1455-87)	1 coat 80 - 85
Heel mark resistance	Very good
Leveling	Excellent
pH	8.1 - 8.9
Powdering resistance	Excellent
Recoat	Excellent
Dry time	20-30 min