Customer Service: 1-888-GO-BETCO
Equipment Tech Support 1-877-856-5954
8AM - 5:30PM EST, Monday - Friday

Finish 101™ Floor Finish



Acrylic Polymer Floor Finish
This floor finish delivers both optimal value and performance and is developed specifically for facilities that desire to contain floor maintenance costs. Education and retail facilities will realize savings to their bottom line, while also meeting bid specifications. This formula is designed for low maintenance programs where burnishing is minimal or unavailable. Great off the mop gloss, quick build and superior leveling make this floor finish easy to apply.

Features

Optimal value and performance.
Reduced labor - Fast build with fewer coats.
Deep gloss.
0.0% Free Styrene

Available In

4 - 1 Gal. Bottles Item #69604-00

55 Gal. Drum Item #69655-00

5 Gal Bag in Box Item #696B5-00

Directions for Use

Recommended for use on all types of resilient tile flooring and properly prepared hard surfaces.

RESTORATIVE MAINTENANCE: Completely remove all old wax, finish and soil from floor surface following strip procedure instructions on Betco® stripper label. Floor surface must be clean, dry and free of residue before finish is applied. Rinse with clean water if necessary. Apply floor finish in uniform, thin to medium coats using a clean synthetic finish mop, microfiber mop or applicator system. Allow each coat to dry thoroughly before applying additional coats, usually 20 - 30 minutes. Elevated temperatures, heavy coats and humidity may extend dry time. A minimum of 4 coats of finish is recommended. Note: This product is a self-sealing finish, however, if tile is old, worn or porous, initially applying 1 - 2 coats of a Betco sealer will enhance gloss and long term performance.

ROUTINE MAINTENANCE: Sweep large debris and dust mop. Damp mop or automatic scrub using a Betco floor cleaner. Buff or burnish the floor to enhance gloss as needed. Use Betco® One Step High Speed Cleaner/Restorer to condition the floor and extend the time between top scrub and recoating.

INTERIM MAINTENANCE: Sweep large debris and dust mop. Top scrub the floor using Daily Scrub SC and maroon pad or equivalent to remove the top soiled layers of finish. Floor surface must be clean, dry and free of residue before finish is applied. Apply 1 - 2 coats of finish as directed above.

Please recycle empty containers. Note: Slip resistance meets or exceeds standard, (ASTM D 2047-11) James Machine 0.5 minimum.

Tech Specs

Color (dried)	Crystal clear
Color (liquid)	White
Coverage	2000 square feet/gallon
Dry time	20 -30 minutes
Fragrance	Mild
Freeze/thaw stability	3 cycles
Leveling	Excellent
pH	8.1 - 8.9
Gloss (ASTM D 1455-87)	1 coat 75 - 80 2 coats 80 - 85
Heel mark resistance	Excellent
Powdering resistance	Excellent
Recoat	Excellent
Specific gravity	1.03
Warranty	2 years