

# Hydroline® Sealer Floor Sealer



## Waterbased Wood Floor Sealer

General use, single-component waterbased sealer ideal for sports and residential floors.

### Features

- Fast drying.
- Easy to apply.
- Great for maple floors.
- VOC compliant.
- No catalyst required.

### Available In

**4 - 1 Gal. Bottles F-Style Item #B0656-4312**

**5 Gal. Pail Item #B0656-0512**

### Directions for Use

Read the entire label before using this product.

**PREPARATION:** FOR NEW OR SANDED finish: Prepare the finish using accepted NOFMA or MFMA procedures. Vacuum all dust and tack with cotton towel. Apply water-based wood sealer following instructions on sealer label: 2 coats minimum.

**FOR SCREENING AND RECOATING:** Always clean the finish prior to screening. Mix wood finish maintenance cleaner at 32 oz./gal. or 250 mL/L (1:4) with water and tack using a clean towel. Screen using new 100 or 120 grit screens, vacuum and tack using a water moistened cotton towel. **APPLICATION:** Shake or mix container before opening. While stirring product, add catalyst slowly and continue mixing for 30 seconds. Mix thoroughly and let stand for 5 minutes. Once catalyzed, pot life is 24 hours. Apply at 700 - 850 sq.ft./gal. Allow to dry thoroughly (minimum 3 hours between coats depending on conditions with a maximum of 6 hours). Abrade between coats if 6 hours has elapsed with a maroon top scrub pad or 120 grit screen. Apply 2 coats minimum. Allow light traffic after 24 hours, however, it is susceptible to scuffing and marring. **NOTE:** Allow adequate ventilation. Circulate air above the finish. Allow adequate air finish hours for at least 24 hours after final coat is applied. Use air conditioners and exhaust fans where available.

**MAINTENANCE:** DAILY MAINTENANCE: Dust mop using water-based dust mop treatment (see product label for additional instructions). Dust mop as often as possible, at least once per day. WEEKLY MAINTENANCE: Tack (deep clean) the finish using wood finish maintenance cleaner (see product label for additional instructions). Tack frequently, but at least once a week. Refer to the Water-Based Wood Coatings Application & Procedure Guide for detailed instructions. **NOTE:** Slip resistance meets or exceeds (ASTM D 2047-04) James Machine 0.5 minimum.

### Tech Specs

Color	Clear
Coverage	600 sq. ft./gal
Dry time	2 - 3 hours
Recoat Window	2 - 24 hours
Pot life	NA
Warranty	1 year
Light traffic	24 hours
Full cure	7 days
Rugs	2 weeks
VOC	Less than 250 grams/liter