

EasyStreet™ Floor Finish



One Component Clear Waterbased Wood Floor Finish

EasyStreet provides outstanding durability and clarity without the need of an external catalyst. EasyStreet's superior wear properties, low odor and ease of application make it perfect for Commercial, Residential and Sports Floors.

Features

- One Component, Unlimited Pot Life
- Colorless, Clear Film Clarity
- Non-yellowing formula, finish will not amber over time
- Outstanding Durability
- Low Non-Offensive Odor
- Superior Flow, Leveling and Low Foam Formula

Available In

Gloss 4 - 1 Gal. F-Style Item #B1655-4312

Satin 4 - 1 Gal. F-Style Item #B1657-4312

Satin 5 Gal. Pail Item #B1657-0512

Semi-Gloss 4 - 1 Gal. F-Style Item #B1656-4312

Super Matte 4 - 1 Gal. F-Style Item #B1658-4312

Directions for Use

PREPARATION: FOR NEW OR SANDED FLOORS: Prepare the floor using accepted NWFA or MFMA procedures. Vacuum all dust and tack with cotton towel. All residue must be removed. Apply water-based wood sealer following instructions on sealer label: 2 coats minimum.

FOR SCREENING AND RECOATING: Always clean the floor prior to screening. Mix GT Cleaner at 32 oz./gal. or 250 mL/L (1:4) with water and tack using a clean towel. Screen using new 100 or 120 grit screens or higher, vacuum and tack using a water moistened cotton towel.

APPLICATION: Mix finish 1 minute; apply at 550 - 700 sq.ft./gal. Pour finish into a clean, dry, plastic pour can. Pour a 4-inch wide line of finish along one wall with the grain of the wood. With applicator at a slight angle, move the puddle line to the opposite wall, always maintaining a wet edge. At the end of each pass, make a smooth turn with the applicator and squeeze out excess finish with the grain next to the puddle line. Allow to dry thoroughly (minimum 2 hours between coats depending on conditions with a maximum of 24 hours). Abrade between coats if 24 hours has elapsed with a maroon top scrub pad or 120 grit screen. Apply 2 coats minimum. Allow light traffic after 24 hours, however, it is susceptible to scuffing and marring.

Please recycle empty containers. NOTE: Allow adequate ventilation. Circulate air above the floor. Allow adequate airflow for at least 24 hours after final coat is applied. Use air conditioners and exhaust fans where available.

Tech Specs

Color	Crystal Clear
Coverage	550-700 sq. ft./gal
Dry time	2-3 hrs. between coats.
Recoat time	2 – 24 hours
Warranty	1 year
VOC	<275 g/l
Light traffic	24 hours
Full cure	7 days
Rugs	2 weeks