

Sure Cure™ Floor Sealer and Finish



Acrylic Urethane Sealer - Finish

This advanced water-based urethane sealer and finish redefines hard surface floor care. Designed for versatility, it applies effortlessly to VCT, concrete (new or old), slate, quarry tile, cementitious or epoxy terrazzo, and marble. Its powerful formula resists a wide range of chemicals while delivering outstanding durability and a beautiful finish. With simple maintenance and no need for etching before application, achieving long-lasting protection has never been easier.

Features

Versatile - Adheres to a variety of hard surface floors.
Long lasting - Protection and abrasion resistance.
Strippable.
Labor saving - High solids requires fewer coats.

Available In

4 - 1 Gal. Bottles Item #60904-00

55 Gal. Drum Item #60955-00

5 Gal Bag in Box Item #609B5-00

Directions for Use

Recommended for use on all types of stone flooring (brick, marble, slate, all terrazzo, concrete-new and old), resilient tile, quarry and non-glazed ceramic tile.

RESTORATIVE MAINTENANCE:

Completely remove all old wax, finish and soil from floor surface following strip procedure instructions on Betco stripper label. Floor surface must be clean, dry and free of residue before finish is applied. Rinse with clean water if necessary. Apply finish in uniform, thin to medium coats using a clean synthetic finish mop, microfiber mop or applicator system. Allow each coat to dry thoroughly before applying additional coats, usually 30 - 45 minutes. Elevated temperatures, heavy coats and humidity may extend dry time. A minimum of 4 coats of finish is recommended.

ROUTINE MAINTENANCE:

Sweep large debris and dust mop. Damp mop or automatic scrub using a Betco floor cleaner. Buff or burnish the floor to enhance gloss as needed. Use Betco One Step High Speed Cleaner/Restorer to condition the floor and extend the time between top scrub and recoating.

INTERIM MAINTENANCE:

Sweep large debris and dust mop. Top scrub the floor using Daily Scrub SC and blue or green pad to remove the top soiled layers of finish. Floor surface must be clean, dry and free of residue before finish is applied. Apply 1 - 2 coats of finish as directed above. Please recycle empty containers.

CONCRETE APPLICATION:

May be applied to new concrete after 30 days (fully cured) and a surface temperature above 50 °F. Prior to applying sealer to new concrete, use an acidic solution to neutralize excess alkalinity. All new concrete must be cleaned and rinsed. Not for use outdoors. Old concrete must be cleaned with a degreasing solution and rinsed for proper adhesion.

GLAZED TILE/POLISHED SURFACES:

1. Test in an inconspicuous area first, proper adhesion may be difficult due to lack of porosity.

Note: Slip resistance meets or exceeds standard, (ASTM D 2047-11) James Machine 0.5 minimum.

Tech Specs

| | |
|-----------------------|---|
| Color (dried film) | Clear |
| Color (liquid) | Milky white |
| Coverage | 1500 - 2000 square feet/gallon |
| Drying time | 30 - 45 minutes under normal conditions |
| Durability | Excellent |
| Flash Point | None |
| Fragrance | Mild |
| Freeze/thaw stability | protect from freezing |
| Initial gloss | High |
| Leveling | Excellent |
| pH | 8.4 - 8.9 |
| Recoatibility | Very good |

