

Player's Choice™ One Wood Floor Finish



Clear Waterbased Sport Floor Finish

Player's Choice™ One is a one component clear waterbased sport finish specifically formulated for sports floor applications. Player's Choice One provides a completely colorless finish with exceptional durability and chemical resistance without the use of an external catalyst.

Features

- One Component
- Colorless, Clear Finish Clarity
- Excellent Chemical and Perspiration Resistance
- Easy to Maintain
- Superior Flow, Low Foam and Odor Formula

Available In

5 Gal. Pail Item #B165905-12

4 - 1 Gal. Bottles F-Style Item #B165943-12

Directions for Use

PREPARATION: FOR NEW OR SANDED FLOORS: Prepare the floor using accepted NWFA or MFMA procedures. Vacuum all dust and tack with cotton towel. All residue must be removed. Apply water-based wood sealer following instructions on sealer label: 2 coats minimum.

FOR SCREENING AND RECOATING: Always clean the floor prior to screening. Mix Squeaky Cleaner at 32 oz./gal. or 250 mL/L (1:4) with water and tack using a clean towel. Screen using new 100 or 120 grit screens or higher, vacuum and tack using a water moistened cotton towel.

APPLICATION: Mix finish 1 minute; apply at 550 - 700 sq.ft./gal. Pour finish into a clean, dry, plastic pour can. Pour a 4-inch wide line of finish along one wall with the grain of the wood. With applicator at a slight angle, move the puddle line to the opposite wall, always maintaining a wet edge. At the end of each pass, make a smooth turn with the applicator and squeeze out excess finish with the grain next to the puddle line. Allow to dry thoroughly (minimum 2 hours between coats depending on conditions with a maximum of 24 hours). Abrade between coats if 24 hours has elapsed with a maroon top scrub pad or 120 grit screen. Apply 2 coats minimum. Allow light traffic after 24 hours, however, it is susceptible to scuffing and marring.

Please recycle empty containers. NOTE: Allow adequate ventilation. Circulate air above the floor. Allow adequate airflow for at least 24 hours after final coat is applied. Use air conditioners and exhaust fans where available. NOTE: Slip resistance meets or exceeds (ASTM D 2047-11) James Machine 0.5 minimum.

Tech Specs

Color	Crystal Clear
Coverage	600-800 sq. ft./gal
Dry time	2-3 hrs. between coats
Recoat time	2 – 24 hours
Warranty	1 year
VOC	<275 g/l