

BetcoBest® LM Floor Finish



High Build Floor Finish with MMT/50™ Technology

BetcoBest LM floor finish a proven quantum leap in floor care technology. This innovative floor finish utilizes an exclusive patent pending technology from Betco. MMT/50 "Macromolecular Polymer Technology" uniquely combines large (macro) polymers with the highest solid content and a low viscosity to provide the most effective labor saving floor finish on the market today. This finish maintains a high gloss with minimal burnishing and fewer coats than conventional products.

Features

- Fewer coats reduce labor.
- Provides a deep high gloss.
- Built in application indicator makes training easy.
- Patented MMT/50™ formula combines a high solid content and low viscosity for fewer coats.

Available In

4 - 1 Gal. Bottles Item #64404-00

5 Gal. Pail Item #64405-00

55 Gal. Drum Item #64455-00

2 - 1.25 Gal. Quickcoat Item #64459-00

Directions for Use

Recommended for use on all types of resilient tile flooring and properly prepared hard surfaces.

RESTORATIVE MAINTENANCE:

Completely remove all old wax, finish and soil from floor surface following strip procedure instructions on Betco's stripper label. Floor surface must be clean, dry and free of residue before finish is applied. Rinse with clean water if necessary. Apply finish in uniform, medium to medium-heavy coats using a clean synthetic finish mop, microfiber mop or applicator system. Allow each coat to dry thoroughly before applying additional coats, usually 30 - 40 minutes. 2 - 3 coats are recommended. NOTE: This product contains an opaque application indicator that will clarify when drying. This is a self-sealing finish; however, if tile is old, worn or porous a Betco floor sealer can be used.

ROUTINE MAINTENANCE:

Sweep large debris and dust mop. Damp mop or automatic scrub using a Betco floor cleaner. Buff or burnish the floor to enhance gloss as needed. Use Betco's One Step High Speed Cleaner/Restorer to condition the floor and extend the time between top scrub and recoating.

INTERIM MAINTENANCE:

Sweep large debris and dust mop the floor. Top scrub the floor using Daily Scrub SC and maroon pad to remove the top soiled layers of finish. Floor surface must be clean, dry and free of residue before finish is applied. Apply 1 - 2 coats of finish as directed above.

Please recycle empty container. NOTE: Slip resistance meets or exceeds (ASTM D 2047-11) James Machine 0.5 minimum.

Tech Specs

Color (dried film)	Crystal Clear
Color (wet)	Opaque
Color (liquid)	Opaque
Coverage	2,000 - 3,000 sq. ft./gallon
Dry time	20 - 30 minutes
Fragrance	Mild
Heel mark resistance	Excellent
Leveling	Excellent
pH	9
Powdering resistance	Excellent
Warranty	2 years