

# Player's Choice™ OMU 350 Floor Finish



## Urethane Gloss Finish for Wood Gym Floors

Time proven and tough, this oil-based formulation represent the ultimate in durability. Easy to apply with a standard or gravity feed applicator Player's Choice™ OMU 350 levels to a consistent smooth shine and enhances the natural beauty of the wood. Player's Choice™ OMU 350 is 350 VOC compliant.

### Features

- 54% solids urethane
- Excellent flow and leveling
- Superior Durability
- Great depth of gloss

### Available In

**5 Gal. Pail Item #B069805-12**

### Directions for Use

Recommended for use in finishing all types of wood floors (gymnasium, sports floors, maple and oak). **FOR NEW OR SANDED FLOORS:** NOTE: Always use a respirator when applying this product. 1. Sand the floor using accepted NWFA or MFMA procedures. All old finish must be removed. 2. Finish sanding with 100 or 120 grit screens. 3. Vacuum all dust and tack the floor with dry cotton towels. Repeat tacking if necessary. 4. Apply 2 coats of a penetrating sealer. Follow recommended application procedures for penetrating sealer. 5. Screen seal coat(s) with 120 grit screens, vacuum and tack with waterless cleaner. Let tack dry 30 - 60 minutes with good ventilation before applying paint or finish. 6. Apply finish. Use a lambs wool applicator first across the grain and then with the grain or use a gravity feed applicator applying the product with the grain of the wood. 7. Apply at 400 - 450 sq.ft./gal. 8. Make sure the product is dry before recoating. Abrade between coats with maroon top scrub pad or used screens. 9. Let dry at least 72 hours before allowing normal traffic. 10. All paints should be tested prior to use for compatibility and adhesion. **PREVIOUSLY SEALED OR FINISHED FLOORS:** 1. Tack floor using cotton towels and waterless cleaner. 2. Screen with 100 grit screens with the grain of the wood. 3. Vacuum all dust and tack the floor with cotton towels and waterless cleaner. Repeat tacking if necessary. Let tack dry before coating. 4. Apply with lambs wool applicator first across the grain and then with the grain or use a gravity feed applicator applying the product with the grain of the wood. 5. Apply at 400 - 450 sq.ft./gal. 6. Make sure the product is dry before recoating. Abrade between coats with a maroon top scrub pad or used screen. 7. Let dry at least 72 hours before allowing normal traffic. 8. All paints should be tested prior to use for compatibility and adhesion. NOTE: Do not use on resilient tile. Use waterless cleaner for clean up. Not recommended for floors that have been previously maintained with wax or oil.

### Tech Specs

Color	Amber
Coverage	450-500 sq. ft./ gal
Dry/ Recoat Time	12-24 hours
Warranty	1 year
Light traffic	48 hours
Full cure	30 days
VOC	Less than 350 grams/liter
Solids	54% +/-