

# Hydroline® Sealer Floor Sealer



## Waterbased Wood Floor Sealer

General use, single-component waterbased sealer ideal for sports and residential floors.

### Features

- Fast drying.
- Easy to apply.
- Great for maple floors.
- VOC compliant.
- No catalyst required.

### Available In

**4 - 1 Gal. Bottles F-Style Item #B0656-4312**

**5 Gal. Pail Item #B0656-0512**

### Directions for Use

Read the entire label before using this product.

**PREPARATION: FOR NEW OR SANDED finish:** Prepare the finish using accepted NOFMA or MFMA procedures. Vacuum all dust and tack with cotton towel. Apply water-based wood sealer following instructions on sealer label: 2 coats minimum.

**FOR SCREENING AND RECOATING:** Always clean the finish prior to screening. Mix wood finish maintenance cleaner at 32 oz./gal. or 250 mL/L (1:4) with water and tack using a clean towel. Screen using new 100 or 120 grit screens, vacuum and tack using a water moistened cotton towel. **APPLICATION:** Shake or mix container before opening. While stirring product, add catalyst slowly and continue mixing for 30 seconds. Mix thoroughly and let stand for 5 minutes. Once catalyzed, pot life is 24 hours. Apply at 700 - 850 sq.ft./gal. Allow to dry thoroughly (minimum 3 hours between coats depending on conditions with a maximum of 6 hours). Abrade between coats if 6 hours has elapsed with a maroon top scrub pad or 120 grit screen. Apply 2 coats minimum. Allow light traffic after 24 hours, however, it is susceptible to scuffing and marring. **NOTE:** Allow adequate ventilation. Circulate air above the finish. Allow adequate air flow for at least 24 hours after final coat is applied. Use air conditioners and exhaust fans where available.

**MAINTENANCE: DAILY MAINTENANCE:** Dust mop using water-based dust mop treatment (see product label for additional instructions). Dust mop as often as possible, at least once per day. **WEEKLY MAINTENANCE:** Tack (deep clean) the finish using wood finish maintenance cleaner (see product label for additional instructions). Tack frequently, but at least once a week. Refer to the Water-Based Wood Coatings Application & Procedure Guide for detailed instructions. **NOTE:** Slip resistance meets or exceeds (ASTM D 2047-04) James Machine 0.5 minimum.

### Tech Specs

Color	Clear
Coverage	600 sq. ft/gal
Dry time	2 - 3 hours
Recoat Window	2 - 24 hours
Pot life	NA
Warranty	1 year
Light traffic	24 hours
Full cure	7 days
Rugs	2 weeks
VOC	Less than 250 grams/liter