

# Player's Choice™ OMU 450 Floor Finish



## Oil-Based Wood Floor Finish

Player's Choice™ from Basic Coatings is a durable oil-modified urethane wood floor finish designed to protect wood floors while providing a rich, attractive appearance.

### Features

- Rich, attractive oil-based finish
- Easy to apply; excellent flow and leveling
- Excellent mar and scuff resistance
- For sports, commercial and residential application

### Available In

**5 Gal. Pail Item #B0699-0512**

### Directions for Use

Recommended for use in finish all types of floors (gymnasium, sports floors, maple and oak).

FOR NEW OR SANDED floors: NOTE: Always use a respirator when apply this product. Sand the floors or use accepted NFWA or MFMA procedures. All finish must be removed. Finish sand with 100 or 120 grit screens. Vacuum all dust and the floors or with dry cotton towels. Repeat if necessary. 4. Apply 2 coats of a penetration sealer. Recommended application procedures for penetration sealer. 5. screen seal oat(s) with 120 grit screens, vacuum and with waterless cleaner Let dry 30 - 60 minutes with ventilation before apply paint or finish. 6. Apply finish. Use a lambs applicator fi rest across the grain and then with the grain or use a gravity feed applicator apply the product with the grain of the. 7. Coats of finish are recommended. Apply at 400 - 450 sq./gal. 8. Allow to dry at least 12 hours before recoat Abrade between coats with maroon top scrub pad or used screens. 9. Let dry at least 72 hours before allow normal traffic. 10. All paints should be tested prior to use for compatibility and adhesion.

PREVIOUSLY SEALED OR FINISHED floors: Floors or use cotton towels and waterless cleaner 2. screen with 100 grit screens or a maroon pad/SPP pad with the grain of the. Vacuum all dust and the floors or with cotton towels and waterless cleaner repeat if necessary. Let dry before coat 4. Apply with lambs applicator fi rest across the grain and then with the grain or use a gravity feed applicator apply the product with the grain of the. This coat an also be applied with a T-bar. 5. T coats of finish are recommended. Apply at 400 - 450 sq./gal. 6. Allow to dry at least 12 hours before recoat. Abrade between coats with a maroon top scrub pad or used screen. 7. Let dry at least 72 hours before allow normal traffic. 8. All paints should be tested prior to use for compatibility and adhesion. NOTE: Do not use on resilient tile. Use waterless cleaner for cleanup. Not recommended for floors that have been previously maintained with wax or oil.

### Tech Specs

Warranty	1 year
Light traffic	24 hours
Rugs	30 days
VOC	Less than 450 grams/liter
Solids	50% +/-
Color	Light Amber
Coverage	400 - 800 sq. ft/gal (10 - 20 sq. M/L)
Dry time	12 -18 hours
Full cure	72 hours