Customer Service: 1-888-GO-BETCO
Equipment Tech Support 1-877-856-5954
8AM - 5:30PM EST, Monday - Friday

BetcoBest® LM Floor Finish with SRT™

New & Improved! High Build Floor Finish
BetcoBest LM is the most effective labor-saving finish on the market! MMT/50™ Macromolecular Polymer Technology uniquely combines large polymers with the highest solid content and a low viscosity to slash strip/refinish and top scrub/recoat time, labor, and overall cost! This product also maintains a high gloss with minimal burnishing and fewer coats than conventional finishes

Features

40% less labor compared to conventional finishes
Requires half the coats of conventional finish
$1,000 saved on average per location per strip/refinish project
50% higher gloss with fewer coats, even with minimal burnishing
Scuff-Resistant Technology (SRT™) resists black heel marks

Available In

4 - 1 Gal. Bottles Item #64404-00

55 Gal. Drum Item #64455-00

5 Gal Bag in Box Item #644B5-00

Directions for Use

Recommended for use on all types of resilient tile flooring and properly prepared hard surfaces.

RESTORATIVE MAINTENANCE:
Completely remove all old wax, finish and soil from floor surface following strip procedure instructions on Betco stripper label. Floor surface must be clean, dry and free of residue before finish is applied. Rinse with clean water if necessary. Apply finish in uniform, medium to medium-heavy coats using a clean synthetic finish mop, microfiber mop or applicator system. Allow each coat to dry thoroughly before applying additional coats, usually 30 - 40 minutes. 2 - 3 coats are recommended.
NOTE: This product contains an opaque application indicator that will clarify when drying. This is a self-sealing finish; however, if tile is old, worn or porous a Betco floor sealer can be used.

ROUTINE MAINTENANCE:
Sweep large debris and dust mop. Damp mop or automatic scrub using a Betco floor cleaner. Buff or burnish the floor to enhance gloss as needed. Use Betco One Step High Speed Cleaner/Restorer to condition the floor and extend the time between top scrub and recoating.

INTERIM MAINTENANCE:
Sweep large debris and dust mop the floor. Top scrub the floor using Daily Scrub SC and maroon pad to remove the top soiled layers of finish. Floor surface must be clean, dry and free of residue before finish is applied. Apply 1 - 2 coats of finish as directed above.

Please recycle empty container. NOTE: Slip resistance meets or exceeds (ASTM D 2047-11) James Machine 0.5 minimum.

Tech Specs

Color (dried film)	Crystal Clear
Color (wet)	Opaque
Color (liquid)	Opaque
Coverage	2,000 - 3,000 sq. ft./gallon
Dry time	20 - 30 minutes
Fragrance	Mild
Heel mark resistance	Excellent
Leveling	Excellent
pH	9
Powdering resistance	Excellent
Warranty	2 years