

# StreetShoe® NXT Wood Floor Finish



## Water-Based High Traffic Wood Floor Finish

StreetShoe®#174; NXT is the fastest curing finish on the market today and an industry benchmark for waterbased finishes. StreetShoe NXT provides a clear finish that is unmatched in performance and durability. StreetShoe NXT also contains UV inhibitors to protect against harmful rays from the sun.

### Features

- Fast curing - "Coat Today, Play Tomorrow"
- Fast Drying - 2-3 hours
- The industry standard for durability
- High Gloss
- UV inhibitor

### Available In

**5 Gal. Pail w/ Catalyst Item #166405-00**

**4 - 1 Gal. Bottles F-Style w/Catalyst Item #B166443-12**

### Directions for Use

**PREPARATION: FOR NEW OR SANDED FLOORS:** Prepare the floor using accepted NWFA or MFMA procedures. Vacuum all dust and tack with cotton towel. All residue must be removed. Apply water-based wood sealer following Betco Waterbased Wood Floor Coating Application Procedures.

**FOR SCREENING AND RECOATING:** Always clean the floor prior to screening. Mix Squeaky Cleaner at 32 oz./gal. or 250 mL/L (1:4) with water and tack using a clean towel. Screen using new 100 or 120 grit screens or higher, vacuum and tack using a water moistened cotton towel.

**APPLICATION:** While stirring product, add catalyst slowly and continue mixing for 30 seconds. Mix thoroughly and let stand for 10 minutes. Once catalyzed, pot life is 24 hours. Apply at 500 - 700 sq.ft./gal. Pour finish into a clean, dry, plastic pour can. Pour a 4-inch wide line of finish along one wall with the grain of the wood. With applicator at a slight angle, move the puddle line to the opposite wall, always maintaining a wet edge. At the end of each pass, make a smooth turn with the applicator and squeeze out excess finish with the grain next to the puddle line. Allow to dry thoroughly (minimum 3 hours between coats depending on conditions with a maximum of 24 hours). Abrade between coats if 24 hours has elapsed with a maroon top scrub pad or high grit or used screen. Apply StreetShoe NXT per directions for use. Allow light traffic after 24 hours, however, it is susceptible to scuffing and marring.

Please recycle empty containers. NOTE: Allow adequate ventilation. Circulate air above the floor. Allow adequate airflow for at least 24 hours after final coat is applied. Use air conditioners and exhaust fans where available. NOTE: Slip resistance meets or exceeds (ASTM D 2047-11) James Machine 0.5 minimum.

### Tech Specs

Color	Crystal Clear
Coverage	600-800 sq. ft./gal
Dry time	2-3 hrs. between coats
Pot life	24 hrs.
VOC	<150 g/l
Defoaming	Excellent
Leveling	Excellent
Chemical Resistance	Excellent
Odor	Mild
Clean Up	Water
Slip Resistance	Meets/Exceeds ASTM D-2047
Warranty	1 year